INSTALLATION AND MAINTENANCE ADVICE

SERIES:
DIN

NOMINAL SIZE:
15x15 cm glazed ceramic
7,4x15 cm glazed ceramic
7,4x7,4 cm tesserae glazed ceramic on net
3,6x7,4 cm tesserae glazed ceramic on net

USE:
Walls & floors
indoors

INSTALLATION:
Install on perfectly flat and dry floors and walls. Adapt the radii of edges and corners of the substrate and apply an adequate quantity of adhesive with a notched trowel to allow the correct positioning of the special pieces on the substrate.

IMPORTANT

Given the artisan nature of the collection, it is strongly recommended, before carrying out the final laying of the material, to dry lay the different formats, in order to evaluate the correct positioning of the various elements and to harmonize the tiling by means of a careful subdivision of the joints.

RECOMMENDED ADHESIVE:
NON-RAPID-DRYING adhesive for porcelain stoneware to make it easier to fix the sheets.

RECOMMENDED JOINT:
Place the sheets with the same joint as within the sheet

RECOMMENDED FILLERS:
CEMENT-BASED GROUT: Grout 0.5 m2 at a time and wash thoroughly with clean water. Remove all traces of grout carefully before it dries completely.
EPOXY GROUT: Grout 0.5 m2 at a time and wash thoroughly with clean water. Remove all traces of grout carefully before it dries completely.

Ceramiche Mutina Spa
Via del Crociale 25
41042 Fiorano, MO Italia
T +39 0536 812800
F +39 0536 812808
C.F. / P.I. 00336880364
mutina.it

CLEANING AT THE END OF THE WORK:

CEMENT-BASED GROUT: Buffered acid (e.g. DETERDEK PRO by FILA or similar). Wet the floor with water, dilute the product 1:5 with water and pour it on the floor. Wait for 2-3 minutes then use a white scotch brite pad and rinse well with clean water.

EPOXY GROUT: Alkaline detergent (e.g. FILA CR10 by FILA). FILA CR10: apply pure, wait for 30 minutes then use a green scotch brite pad.

SILICONE: Solvent for silicone e.g. FILA ZERO SIL. Put it straight onto the stain, wait for 20 minutes and remove the mark using scotch brite.

PAINT: Can usually be removed using water, but if resin-based paints or particular enamels have been used, it is best to ask the manufacturer which solvent is most suitable.

RUST: stain remover es. FILA NO RUST. Apply the product onto the stain, leave for 15 minutes, remove the residue and rinse thoroughly.

Ceramiche Mutina Spa
Via del Crociale 25
41042 Fiorano, MO Italia
T +39 0536 812800
F +39 0536 812808
C.F. / P.I. 00336880364
mutina.it